BERGER PRODUCT SPECIFICATIONS

BERGER DURACAST UNDERCOAT

Silicate Based Primer

PRODUCT DESCRIPTION	It is inorganic silicate based premium grade two component, high build, undercoat specially formulated to prepare the substrate for good bonding of stone texture coatings.					
	Superior adhesion to the substrate					
	Good opacity and sealing properties					
	Washable and suitable for exterior application					
	Very good algae and alkaline resistance properties					
		rs for groove creation				
	 Environment friend 	lly product				
DESIGN USE		oncrete, plaster, bri ace should be pain				
PHYSICAL DATA	WEIGHT SOLIDS	75 ± 3	%			
	FINISH	Matt				
	DRY FILM THICKNES	S (DFT) 100 –	200 microns			
	WET FILM THICKNESS (WFT) 250 – 500 microns					
	NUMBER OF COATS 1					
	THEORETICAL COVERAGE 2 – 2.5 sq. mtrs/Kg					
	COLOUR RANGE White / Grey / Black					
	NO. OF COMPONENTS Two					
	STANDARD PACKING SIZE 26 Kgs					
APPLICATION METHOD	Conventional Air Spray This is the recommended method of application The tip size and air pressure should be adjusted / varied to obtain the desired texture size and pattern.					
				ittern.		
	Ambient	the desired t	exture size and pa			
DRYING TIME	Ambient Temperature			Overcoatir	•	
DRYING TIME	Temperature	the desired t	exture size and pa		Maximum	
DRYING TIME	Temperature 15 °C	the desired t	exture size and pa	Overcoatir Minimum 36 hours	Maximum Indefinite	
DRYING TIME	Temperature	the desired t Touch Dry 8 hours	exture size and pa Hard Dry 36 hours	Overcoatir Minimum	Maximum	
DRYING TIME	Temperature 15 °C 25 °C	the desired t Touch Dry 8 hours 4 hours	exture size and pa Hard Dry 36 hours 30 hours	Overcoatir Minimum 36 hours 30 hours	Maximum Indefinite Indefinite	
	Temperature 15 °C 25 °C	the desired t Touch Dry 8 hours 4 hours 2 hours	exture size and pa Hard Dry 36 hours 30 hours	Overcoatir Minimum 36 hours 30 hours	Maximum Indefinite Indefinite	
DRYING TIME ADDITIONAL INFORMATION	Temperature 15 °C 25 °C 35 °C Thinner	the desired t Touch Dry 8 hours 4 hours 2 hours Not re	exture size and pa Hard Dry 36 hours 30 hours 24 hours	Overcoatir Minimum 36 hours 30 hours 24 hours	Maximum Indefinite Indefinite	
ADDITIONAL	Temperature 15 °C 25 °C 35 °C Thinner Thinning Ratio	the desired t Touch Dry 8 hours 4 hours 2 hours Not re	exture size and pa Hard Dry 36 hours 30 hours 24 hours quired.	Overcoatir Minimum 36 hours 30 hours 24 hours	Maximum Indefinite Indefinite	
ADDITIONAL	Temperature 15 °C 25 °C 35 °C Thinner	the desired t Touch Dry 8 hours 4 hours 2 hours Not re 2% ma	exture size and pa Hard Dry 36 hours 30 hours 24 hours quired.	Overcoatir Minimum 36 hours 30 hours 24 hours	Maximum Indefinite Indefinite	

BERGER PRODUCT SPECIFICATIONS

BERGER DURACAST UNDERCOAT

Silicate Based Primer

SURFACE PREPARATION	The service life span and the service performance of this product are directly related to the degree of surface preparation.			
	New concrete should be left for at least 21 days to cure before coating.			
	The moisture content of the concrete surface should be checked and ensured to be below 16% using a reliable moisture meter, such as the Sovereign Moisture Meter.			
	The surface to be coated must be clean and free from all loose extraneous materials such as loose paint, dust etc.			
	If fungus or algae is present, first treat with Berger Fungicidal Wash and leave for 24 hours. Then, thoroughly rinse and wash or scrape away all the fungus.			
	If grease is present, clean using a mild detergent or solvent and rinse thoroughly to ensure complete removal of the grease, detergent and solvent.			
	Apply a Duracast Undercoat for better adhesion and performance of the coating system.			
PRODUCT USE RESTRICTIONS	 Not recommended for direct application onto bare concrete / plastered surfaces. A suitable undercoat should be applied first. 			
	• Actual pattern of texture will depend on tip size, spray pressure and dilution factors.			
SAFETY PRECAUTION	Avoid contact with eyes and skin. Wear suitable protective clothing.			
	Ensure that there is adequate ventilation in the area where the product is being applied.			
	In case of fire, blanket flames with foam, carbon dioxide or dry chemicals.			
FIRST AID	Eyes : In the event of accidental splashes, flush eyes with warm water immediately and seek medical advice.			
	Skin : Wash skin thoroughly with soap and water or approved industrial cleaner. Do Not Use solvents or thinners.			
	Inhalation : Remove to fresh air, loosen collar and keep patient rested.			
	Ingestion : In case of accidental ingestion, DO NOT INDUCE VOMITING. Obtain immediate medical attention.			
	For further safety information, please refer to our Material Safety Data Sheet (MSDS)			
DISCLAIMER	The information provided on this data sheet is not intended to be complete and is provided as general advice only. It is the responsibility of the user to ensure that the product is suitable for the purpose for which he wishes to use it. As we have no control over the treatment of the product, the standard of surface preparation of the substrate, or other factors affecting the use of this product, we are not responsible for its performance nor would we accept any liability whatsoever or howsoever arising from the use of this product unless specifically agreed to in writing by us. The information contained in this data sheet may be modified by us from time to time, and without notice, in the light of our experience and continuous product development.			