



BERGER FASTCOAT ENAMEL

High Gloss Alkyd Finish

PRODUCT DESCRIPTION

Alkyd high gloss non yellowing enamel finish especially developed for faster drying requirement for versatile applications.

DESIGN FEATURES

Quick Dry
Non yellowing
Good gloss and colour retention properties with overall durability.
Excellent coverage, flow and levelling properties.
Very good resistance to mild chemicals and solvents
Excellent for marine and industrial application

PHYSICAL CHARACTERISTICS

Recommended Application Data	Wet [μm]	Dry [μm]	m^2/l
Theoretical Coverage	78	25	18

Volume solids	44% (based on ASTM D2697)
Dry Film Thickness Range	25 μm to 35 μm
Flash Point	25 °C
Finish	Gloss
Colour Range	Berger Shade cards/ Fan deck & Fluorescent colours
Standard Packing Size	5 /20 litres

APPLICATION METHOD

BRUSH OR ROLLER	Recommended method of application.
CONVENTIONAL AIR SPRAY	May be used. Dilution of the paint to 18-20 secs on Ford Cup B4 at 30 °C with Solvalux 7-9 to ensure good application properties.
AIRLESS SPRAY	May be used. Tip size : 0.43 – 0.53 mm (17 – 21 thou) Pressure : 110 –160 kg/cm ² (1600 – 2300 psi)

DRYING TIME

Substrate Temperature	Touch Dry	Hard Dry	Overcoating Interval	
			Minimum	Maximum
15 °C	60 minutes	8 hours	24 hours	Indefinite
25 °C	30 minutes	6 hours	6-8 hours	Indefinite
35 °C	15 minutes	4 hours	3-4 hours	Indefinite

USEFUL INFORMATION

THINNER	: SOLVALUX 7-9 (Maximum 5% Addition)
CLEANER	: SOLVALUX 7-9
STORAGE	: Store in a cool dry shaded area.
SHELF LIFE AT 25 °C	: 12 months minimum when stored as prescribed in the MSDS.



SURFACE PREPARATION

The service life span and the service performance of Berger Fastcoat Enamel are directly related to the degree of surface preparation.

- The steel surface coated should be dry, sound and undamaged. It shall be free of surface contaminants such as grease, oil, dust, salts and rust.
- Soluble salts must be removed by washing with fresh water. Dry brushing should be done to remove dirt and dust. If oil or grease is present, clean using mild detergent or solvent and rinse thoroughly.
- If there is evidence of rusting, the affected areas should be thoroughly sand down with sandpaper or mechanical tools to ensure complete removal.
- Use Berger undercoat Primer/Luxol1000/Decoseal as a primer coat and build-coat prior to application of this product is necessary.

To avoid condensation of moisture onto substrate prior to coating application, relative humidity should not exceed 85% and substrate temperature should be more than 3°C above Dew Point.

SUITABLE UNDERCOATS	Berger Fastcoat Primer, Luxaprime 1000, Luxol 1000, Luxol primer range, Decoseal
NOTES	<ul style="list-style-type: none">• The coating specifications given above are typical. For specific recommendations to suit individual applications, please refer to your Berger Paints representative.• Do not over apply this product beyond the recommended film thickness as this may result in extended drying times beyond those quoted overleaf.• This product is designed for spray application only. Other methods of applications, such as brush or roller, may compromise the gloss of the product.

SAFETY PRECAUTION

Avoid contact with eyes and skin. Wear suitable protective clothing such as overalls, goggles, dust mask and gloves. Use barrier cream.

This product contains low flash point solvents, do not use in poorly ventilated areas especially in confined tank interiors.

Ensure that there is adequate ventilation in the area where the product is being applied. Do not breathe in vapour or spray mist.

This product is flammable. Keep away from sources of ignition. Do not smoke.

Take precautionary measures against static discharge.

In case of fire, blanket flames with foam, carbon dioxide or dry chemicals.

FIRST AID

Eyes : In the event of accidental splashes, flush eyes with warm water immediately and seek medical advice.

Skin : Wash skin thoroughly with soap and water or approved industrial cleaner. Do Not Use solvents or thinners.

Inhalation : Remove to fresh air, loosen collar and keep patient rested.

Ingestion : In case of accidental ingestion, DO NOT INDUCE VOMITING. Obtain immediate medical attention.

For further safety information, please refer to our **Material Safety Data Sheet (MSDS)**

DISCLAIMER

The information provided on this data sheet is not intended to be complete and is provided as general advice only. It is the responsibility of the user to ensure that the product is suitable for the purpose for which he wishes to use it. As we have no control over the treatment of the product, the standard of surface preparation of the substrate, or other factors affecting the use of this product, we are not responsible for its performance nor would we accept any liability whatsoever or howsoever arising from the use of this product unless specifically agreed to in writing by us. The information contained in this data sheet may be modified by us from time to time, and without notice, in the light of our experience and continuous product development.